

(12) UK Patent Application (19) GB (11) 2 313 569 (13) A

(43) Date of A Publication 03.12.1997

(21) Application No 9710898.9

(22) Date of Filing 28.05.1997

(30) Priority Data

(31) 08654375

(32) 28.05.1996

(33) US

(71) Applicant(s)

Tecton Products

(Incorporated in USA - Minnesota)

4401 15th Avenue N.W., Fargo, North Dakota 58102,
United States of America

(72) Inventor(s)

R Frank Gunkelman

John C Jambois

(74) Agent and/or Address for Service

Urquhart-Dykes & Lord

8th Floor, Tower House, Merion Way, LEEDS,
LS2 8PA, United Kingdom

(51) INT CL⁶

B29C 69/00 // B29K 101:10 101:12 105:08 105:10, B29L
12:00

(52) UK CL (Edition O)

B5A AA1 A1R2 14E A1R314C1F A1R314C2X A1R456

A2R A20T17 A20T18

B2E EFBA E1108 E1203 E1320 E1327 E1706 E1740

E489T

U1S S1714

(56) Documents Cited

GB 2186833 A

GB 1206946 A

US 4938823 A

US 4394338 A

(58) Field of Search


UK CL (Edition O) B2E EFBA, B5A AA1 AA2 AT17E

INT CL⁶ B29C 47/02 69/00 70/00

Online: WPI

(54) Fibre-reinforced plastic component

(57) A plastic component comprises a fibre-reinforced thermoset substrate and a thermoplastic compound which is bonded directly to the substrate before the substrate is completely cured. The component is formed by (a) pultruding the substrate, whereby fibrous material is wetted out with a thermoset resin and passed through a die 38, (b) forming free radicals (bonding sites) on the surface of the substrate, (c) extruding the thermoplastic onto the substrate so as to form a coating and (d) curing the substrate. Preferably the fibrous material consists of a core of lineal or omnidirectional fibres 12 together with a mat of fibres. The thermoplastic, which is preferably acrylic, may be applied using a crosshead extruder die 48. The bonding sites on the substrate may be formed by flame, corona discharge, spark or plasma treatment. The component is suitable for use in window and door frames.



At least one drawing originally filed was informal and the print reproduced here is taken from a later filed formal copy.

This print takes account of replacement documents submitted after the date of filing to enable the application to comply with the formal requirements of the Patents Rules 1995

GB 2 313 569 A




Fig. 1

Fig. 2





Fig. 3



METHOD OF MANUFACTURE OF A PLASTIC COMPONENT
WHICH IS INSENSITIVE TO THE ELEMENTS, AND A PLASTIC
COMPONENT SO MANUFACTURED

5

Technical Field

The present invention deals with the manufacturing of pultruded plastic components. More particularly, however, the invention deals with a technology wherein pultruded plastic components are manufactured for use in window and door applications and other applications where the component is, in its operating environment, exposed to sunlight, weather, and other deleterious elements. The specific focus of the invention is the manufacture of a fiber-reinforced plastic component provided with a coating which is weather resistant, ultraviolet resistant, durable, and decorative.

Background of the Invention

It has long been recognized that the two most ultraviolet resistant plastic families are acrylics and fluoropolymers. Both plastics have fairly severe drawbacks when their contemplated end use is as a thin weatherable coating. Fluoropolymers are expensive to make. Physically, they are soft, making them very difficult and expensive to use for most outdoor weatherable coating applications.

Acrylics, on the other hand, are relatively inexpensive. Physically they are hard and brittle.

Both fluoropolymers and acrylics have been used in solvent-borne paint systems where they essentially form small pigmented platelets that are held together by some more

suitable backbone resins such as urethanes, latexes, alkyds, etc. While the fluoropolymer and acrylic platelets are ultraviolet resistant, the carrying or backbone resin of the solvent or waterborne coating systems (paint) are not and are, thus, the limiting factor in the serviceable life of these coatings.

Additionally, these systems make extensive use of volatile organic compounds which are regulated as environmental pollutants and are expensive to dispose of. It is also widely known that the weatherability of acrylics increases as the molecular weight of the acrylic increases. However, the melt flow rate (how much flows in a given amount of time at a given temperature and pressure) goes down as molecular weight increases. Thus, the more easily the acrylic is handled (high melt flow), the less optimized it is for weatherability, and also the more brittle it becomes. Thus, the most common weatherable uses of thermoplastic acrylic have been thick sheets of plexiglass having a high molecular weight, such as polymethylmethacrylate (PMMA) (i.e., plexiglass as a thin 2-10 mil calendar rolled film). Normally, these films are calendar rolled with a less brittle, more easily handled, but far less weatherable backing film such as vinyl. For example, high molecular weight PMMA could be nipped between calendaring rolls along with vinyl at temperatures and pressures to form an intimately bonded two layer film 8 mils thick (4 mils each of PMMA and vinyl). In

the first instance, the PMMA is so thick, expensive, and hard to conform to a substrate (process unfriendly), it is not typically used as a weatherable coating. In the second instance, the cost of calendar rolling the acrylic/vinyl film itself, and the cost of the application machinery means that, while the material is much more process friendly, it is normally only feasible to use with a specialty, high value product due to high cost per unit of surface area relative to other coating systems. It is desirable, therefore, to bring together, in a practical manufacturing process, a coating of a thermoplastic acrylic compound chemically bound to a fiber reinforced plastic substrate.

Various industrially manufactured components are, in use, exposed to the elements. Such elements include rain, snow, wind, temperature extremes, ultraviolet radiation, and chemical pollutants. Further, such components can be, from time to time, exposed to various types of impact.

A typical component of this nature is a window frame or a door frame. Typically, such assemblies are made of wood, vinyl or metal. In order to make them more durable and to overcome some of the limitations caused by the elements discussed above, various types of coatings have been developed and methods for applications of such coverings have been conceived.

A first method of forming a product is known as co-extrusion. In this process, a thermoplastic material such as

vinyl is extruded through a forming die to form a profile. Typically, a "capstock", having more expensive pigments, ultraviolet absorbers or blockers, a higher thermoresistance, etc., is concurrently co-extruded to areas that will require
5 greater protection or need a decorative color. Such a "capstock" is a similar thermoplastic material or a compatible thermoplastic.

A second process is known as film wrapping. In this process, a base profile, such as a thermoplastic vinyl
10 extrusion or thermoset pultrusion, is wrapped in a solid, non-molten thermoplastic film. The solid film is, typically, a calendar rolled sheet of two or more plastics (i.e., acrylic and vinyl), and it contains the necessary pigment, ultraviolet absorbers or blockers, etc. The solid film, thereby, provides
15 the protection or decoration to the base profile. In this process, the solid film is secured in place by means of a hot melt or solvent-based adhesive.

A third process known in the art is crosshead extrusion coating or encapsulation. In this process, a profile such as
20 shaped wood is passed through a die which generally conforms to the profile shape. A thermoplastic in flowable form is fed to the die. Typically in this process, the encapsulating material is not required to be adhered to the profile due to the differences in coefficients of thermal expansion.
25 Indeed, it is better if the encapsulating material is not

adhered to the profile due to the difference in coefficients of thermal expansion.

None of these methods, however, overcomes the limitations as previously discussed. In some cases, the process proves to be unwieldy; in other cases, the final product does not prove to be sufficiently durable and resistant to ultraviolet radiation, etc. Other drawbacks are cost and time limitations.

It is to these shortcomings and dictates of the prior art that the present invention is directed. It is a process for the manufacture of a reinforced plastic component (for example, of door and window frames) which overcomes many of the deficiencies of the prior art, and a product made in accordance with the process.

15

Summary of the Invention

The present invention encompasses a plastic component. The component includes a substrate which is formed of a fiber-reinforced, thermoset material. The substrate is die-formed, and a film, of an acrylic compound, is bonded directly to the substrate. Such bonding is accomplished prior to complete curing of the substrate.

In one embodiment of the invention, the substrate includes a core of lineal fibers. The component of that embodiment can further include a mat of fibers which is applied to one side or each of opposite sides of the core of

lineal fibers. The mat(s), and the core of lineal fibers, are wetted out by a resin mixture. In the preferred embodiment, a resin-rich top layer is formed at the surface in contact with the hot forming die.

5 In the preferred embodiment, the substrate is formed using a pultrusion process. The fibers, having been wetted out by a resin mixture, are pultruded through a heated die. The partially cured substrate is then treated to create radicals on the surfaces to be coated.

10 A second, crosshead extrusion die can also be employed. Such a die can be used in the process to apply the melted acrylic compound to the substrate forming a thin weatherable protective film or coating.

The present invention combines a substrate that, due to
15 its near ideal coefficient of thermal expansion (3.4×10^{-6} in./in./degree F), low thermal conductivity, non-corrosiveness, and structural properties (high strength to weight, high stiffness plus the fact that it will not swell with moisture) and its ease and economy of manufacture, make
20 it extremely well-suited for outdoor weatherable applications (such as window and door frames) with the near ideal outdoor weatherable coating (high molecular weight thermoplastic acrylic compounds) to protect the resin system of the pultrusion. The invention does this, minimizing coating
25 material usage by only coating areas exposed to the weather, applying the coating in-line during the pultrusion

manufacturing process, and it does it without adhesives, tie layers or other additional handling or added expense for the disposal of overspray or volatile organic compounds contained in the coating. Additionally, by bonding the acrylic compound
5 coating to an essentially rigid fiber reinforced thermoset substrate, the invention overcomes the problems that acrylics' inherent brittleness normally causes when used as thin coatings.

The invention also comprises a method of forming a
10 reinforced plastic component as described hereinbefore. Such a method includes a first step of forming a substrate by pultruding fibrous material through a first die. The fibrous material, prior to being pultruded through the die, is wetted out with a resin mixture either in a bath or at the entrance
15 of the pultrusion die. After the substrate is formed and partially cured, its surface is treated, and an acrylic compound is applied thereto to form a thin protective, decorative coating on the substrate. The coating is applied directly to the treated, partially-cured substrate by passing
20 the substrate through a crosshead coating die. Simultaneously, the substrate is cured and the acrylic compound coating layer is allowed to chemically bond directly to the substrate.

In a preferred embodiment of practicing the method, the
25 fibrous material includes both lineal and omnidirectional

fibers. Finally, if desired, the acrylic compound coated substrate can be cut to length.

The present invention is thus a method of manufacture of a fiber reinforced plastic component, and a fiber reinforced plastic component so manufactured. More specific features and advantages obtained in view of those features will become apparent with reference to the DETAILED DESCRIPTION OF THE INVENTION, the appended claims, and accompanying drawing figures.

10

Brief Description of the Drawing

Figure 1 is a simplified longitudinal diagram of a process line used in practicing the present method invention;

Figure 2 is a fragmentary section elevational view taken generally along a portion of line 2-2 of Figure 1, greatly enlarged and showing some parts in phantom-lines; and

Figure 3 is a fragmentary section taken generally along line 3-3 of Figure 2.

20

Detailed Description of the Invention

Referring now to the drawings wherein like reference numerals denote like elements throughout the several of views, Figure 1 illustrates a process line 10 used in performing the present method invention. In some respects, the process line 10 is typical of pultrusion lines known in the prior art. For example, a supply 12 of fibers are fed into a carding plate or

preformer 14. As in known processes, the fibers can be both lineal and forming mats of continuous omnidirectional or oriented fibers. Further, a plurality of puller assemblies 16,18 can be provided proximate the output end of the process line 10. At this point in the process, the fibers have already been coated with various agents in accordance with the invention (as will be discussed hereinafter), but they are fed into clamping structures 20,22 of the puller assemblies 16,18 to enable the pieces to be worked to be pulled through the various stations.

The clamps 20,22 are shown as being mounted on reciprocally movable continuous belts 24,26 so that, as a clamp of one puller assembly exerting tension on the material 28 being drawn through the various stages approaches a right spindle 30,32 (as viewed in Figure 1) over which the continuous belt 24,26 carrying the particular clamp 20,22 passes, the tension exerted by the clamp 20,22 on the workpiece 28 being drawn through the stations can be released, and the clamp 20,22 can be moved leftwardly (as viewed in Figure 1) to a location proximate the left spindle 34,36 over which the belt 24,26 carrying the clamp 20,22 passes. Tension can then again be taken upon the workpiece 28 and the particular puller assembly 16,18 can then again effect pulling action.

It will be understood that the operation of the various puller assemblies 16,18 is synchronized. That is, as tension

exerted by the clamp of one puller assembly is released so that the puller assembly clamp can be moved back to the left, the clamp of the other puller assembly will continue to effect pulling action so that the pultrusion process will not be interrupted.

Figure 1 illustrates a first die 38 through which the fibers are drawn after passing through the carding plate or preformer 14. Resin mixture passing through a supply conduit 40 is fed to the die 38 by a feed mechanism 42. The invention contemplates various resin mixtures to be fed to the pultrusion die 38. In accordance with the invention, the media so fed is a thermoset type product. The media selected is one which will not cure completely until after the application of a coating of another media, as will be discussed hereinafter.

Treating of surfaces to be coated is undertaken to create free radicals (bonding sites) on the partially cured substrate's surface. When placed in intimate contact with the molten acrylic compound, the free radicals on the surface of the substrate then chemically bond with available sites in the acrylic compound coating. Treating can be with a flame, via corona discharge, suppressed spark, or, more preferably, plasma treating.

Relatively proximate the pultrusion die 38 along the process line 10, in a direction in which the workpiece moves through the line, is a crosshead extruder die 48. As the

treated fiber reinforced thermoset plastic workpiece 28 is drawn through the crosshead extruder die 48, a molten acrylic compound is fed through a media supply line 50 to the extruder die 48 by an extruder feed mechanism 52. In the extruder die 5 48, the molten acrylic compound is coated directly on the fiber reinforced thermoset, resin matrix. The coating of the acrylic compound is such as to form a fine film. Typically, the acrylic coating would be approximately four mills in thickness.

10 The thermoplastic acrylic is compounded so as to contain many of the properties necessary to make the product being formed more durable. For example, it is desirable that the part, in many applications, be ultraviolet insensitive. Consequently, the acrylic is compounded with ultraviolet 15 blockers or attenuators to achieve this goal. Pigments for color are also compounded. Similarly, the acrylic has properties which render it essentially impervious to the elements of wind, rain, and snow.

A typical application for the product being formed is the 20 frame for a window or door. Consequently, the substrate would be formed in the pultrusion die 38 to a desired profile. It is desirable that only certain surfaces be coated with the acrylic compound. This is so since only certain surfaces of the profile are exposed to the elements, and, by minimizing 25 the extent of coating, cost can be reduced. Consequently, only those surfaces exposed to the elements would be coated

with the acrylic compound in the crosshead extrusion coating die.

In any case, after the acrylic compound is applied, the film formed thereby is bonded directly to the substrate formed
5 in the pultrusion die 38. During and shortly after application of the acrylic compound, curing of the thermoset media continues, and a bonding of the acrylic compound to the fiber reinforced thermoset plastic substrate occurs. Curing continues even to a point at which, if desired, a flying cut-
10 off saw 54 is used to cut the workpiece 28 to desired lengths. The lengths so cut can be positioned on a conveyor 56 for movement for appropriate disposition.

Figures 2 and 3 illustrate, in cross section, a wall of, for example, a window frame manufactured in accordance with
15 the method performed by use of the process line 10 described hereinbefore. Those figures illustrate a substrate which has a core 58 formed from lineal fibers 60. The core 58, in turn, has applied to each of opposite sides thereof a mat 62 of fibers 64. Each of these components is fed from the fiber
20 supply 12 to the carding plate/preformer 14 to position the various fibers in the right orientation prior to being fed into the pultrusion die 38. Prior to entry into, or at the entrance of, the pultrusion die 38, the core 58 and mats 62 are wetted out with a thermoset resin. Figures 2 and 3
25 illustrate a resin-rich layer 66 forming the outer surface of the substrate.

Figures 2 and 3 also show a thin film layer 68 formed on the surface of the resin-rich layer 66 of the substrate. In these particular figures, the acrylic coating 68 is shown as having been applied to the upper surface. This acrylic coating 68, of course, is the coating applied by the crosshead extruder die 48.

It will be understood that various shaped substrates can be formed in accordance with the process. The shape and size of the product will be dictated by the orifice shape and size in the pultrusion die.

It will be understood that this disclosure, in many respects, is only illustrative. Changes may be made in details, particularly in matters of shape, size, material, and arrangement of parts without exceeding the scope of the invention. Accordingly, the scope of the invention is as defined in the language of the appended claims.

What is claimed is:

1. A plastic component, comprising:
 - (a) a die-formed, fiber-reinforced thermoset substrate; and
 - (b) a thermoplastic compound coating bonded directly to said substrate prior to complete curing thereof.
2. A component in accordance with claim 1 wherein said thermoplastic compound coating is acrylic.
3. A component in accordance with claim 2 wherein said substrate includes a core of lineal fibers.
4. A component in accordance with claim 3 wherein said substrate further includes a mat of fibers applied to at least one of opposite sides of said core of lineal fibers, said core of lineal fibers and said at least one mat wetted out with a resin.
5. A component in accordance with claim 4 wherein said substrate is formed using a pultrusion process.
6. A component in accordance with claim 2 wherein said acrylic compound coating is applied to said substrate by means of a crosshead extrusion process.

7. A method of forming a plastic component, comprising the steps of:

(a) forming a substrate by pultruding fibrous material, having been wetted out with a resin bath, through a first die;

(b) treating surfaces of said substrate to form free radicals;

(c) applying an acrylic compound to said treated surfaces of said substrate to form a coating directly thereon by passing the substrate through a crosshead extruder die; and

(d) promoting curing of the substrate and allowing the acrylic compound coating to bond directly thereto.

8. A method in accordance with claim 7 wherein said step of forming the substrate includes pultruding both lineal and omnidirectional fibers.

9. A method in accordance with claim 7 further comprising a step of cutting the acrylic compound coated substrate to length.



Application No: GB 9710898.9
Claims searched: 1-9

Examiner: Gavin Dale
Date of search: 12 August 1997

Patents Act 1977
Search Report under Section 17

Databases searched:

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:

UK Cl (Ed.O): B2E (FBA); B5A (AA1, AA2, AT17E)

Int Cl (Ed.6): B29C 47/02, 69/00, 70/00

Other: Online: WPI

Documents considered to be relevant:

| Category | Identity of document and relevant passage | Relevant to claims |
|----------|---|--------------------|
| X | GB 2186833 (FIBERFORCE LIMITED) See page 1 lines 84-80, page 2 lines 16-22 & 61-64 | 1 |
| X | GB 1206946 (ENGLISH ELECTRIC COMPANY LTD) See Fig 1, page 1 lines 63-68 & page 2 lines 23-39 | 1 at least |
| A | US 4938823 (THE PULTRUSIONS CORPORATION) See column 2 lines 1-5 | 1 |
| X | US 4394338 (MITSUBISHI PETROCHEMICAL CO) See column 2 lines 41-53 | 1 at least |

| | | | |
|---|---|---|--|
| X | Document indicating lack of novelty or inventive step | A | Document indicating technological background and/or state of the art. |
| Y | Document indicating lack of inventive step if combined with one or more other documents of same category. | P | Document published on or after the declared priority date but before the filing date of this invention. |
| & | Member of the same patent family | E | Patent document published on or after, but with priority date earlier than, the filing date of this application. |